



# Soil Property Testing Ltd.

18 Halcyon Court, St Margarets Way, Stukeley Meadows  
Huntingdon, Cambs. PE29 6DG  
Telephone: 01480 455579

## Specification for Highway Works Clause 803 – Granular Sub-base material TYPE 3

### TESTING REQUIRED FOR COMPLIANCE TO EUROPEAN STANDARDS (BS EN 13285)

Grading designation 0/31.5G<sub>P</sub>, Max fines UF<sub>9</sub>, Oversize OC<sub>75</sub>. G<sub>P</sub> (SHW table 8/1)

	Test	Method	Amount required	Compliance	Cost
1	Particle Size Distribution	BS EN 933-1	40kg	Table 8/5	£56.00
2	Determination of Plastic Limit including wet sieve prep passing 0.425mm and Liquid Limit	BS1377:Part2: 1990	20 grams passing 0.425mm	Non Plastic	£24.25
3	Resistance to Fragmentation – Los Angeles Test	BS EN 1097-2	10kg – passing 14mm retained 10mm	LA <sub>50</sub>	£99.00
4	Resistance to Freezing and Thawing – Magnesium Sulphate Soundness Test	BS EN 1367-2	2kg – passing 14mm retained 10mm	MS <sub>35</sub>	£130.00
5	Particle Density Water Absorption Test - up to 5 Fractions:	BS EN 1097-6	10kg	WA <sub>24</sub> NR supplier to state	£47.25 per fraction
6	Testing for Constituent Materials in Recycled Coarse Aggregate and Recycled Concrete Aggregate	BSEN 933-11	20kg	Table 8/3	£130.00
7	Resistance to Wear -Micro Deval Test	BS EN 1097-1	5kg – passing 14mm retained 10mm	M <sub>DE</sub> NR supplier to state	£150.00
8	Water Soluble Sulphate (WS)	BS EN 1744-1	2kg	<300 mg of sulphate (as SO <sub>4</sub> ) per litre	POA
9	Total Sulphur (TS)	BS EN 1744-1	2 -3kg	<1% for aggregates other than air cooled blast furnace slag or 2% for air cooled blast furnace slag	POA
10	Sulphide Content – if required	BS EN 1744-1	2-3kg	<0.06%	POA
<b>OTHER TESTS REQUIRED FOR PARTICULAR CONDITIONS</b>					
A	Frost Heave (If material within 450mm of final road surface) – With Vibrating Hammer compaction	BS812:Part 124	80 Kg (50Kg)	Less than 15mm	POA
B	Volume stability of blast furnace slag Dicalcium Silicate and Iron Disintegration			Free from both	POA
C	Volume stability of steel (BOF & EAF) slags			V <sub>5</sub>	POA
D	All other BS EN 13242 aggregate requirements			N <sub>R</sub>	POA